

TECHNICAL DATA OVERVIEW

DOGLAS® 200LC

Material Description	Composite material made of resin-bonded glass fibers with particularly low thermal conductivity
Colour	beige
Uses	Thermal Insulation Components for Mechanical and Plant Engineering
Availability	Panels, blanks and components/assemblies according to drawings

Physical properties

Properties	Test Standard	Unit	Value
Density	ISO 1183 standard	g/cm ³	1,5
Water absorption	ISO 62 Standard	%	0,2

Thermal properties

Properties	Test Standard	Unit	Value
Application temperature, continuous	–	°C	200
Application temperature, short-term	–	°C	210
Coefficient of linear expansion	DIN 51045	10 ⁻⁶ x K ⁻¹	20
Thermal conductivity	DIN 52612	W/mK	0,13

Mechanical properties

Properties	Test Standard	Unit	Value
Compressive strength at 23 °C	ISO 604 Standard	N/mm ²	330
Flexural strength at 23 °C	ISO 178 Standard	N/mm ²	200
Modulus of Elasticity of Flexural Test	ISO 178 Standard	N/mm ²	10000
Traction	ISO 527 Standard	N/mm ²	80
Splitting force	STANDARD DIN 53463	N	1800

Last Updated: 11/2014

The values shown were determined on standard specimens. The material properties may differ from these values depending on the application and the geometry of the component.

Our consulting engineers and technicians are at your disposal to clarify the exact suitability of the material.